



Open Circuit Voltage vs. State of Charge Comparison* (For Battery Testing)

% Charge	Flooded	Gel	AGM
100%	12.60 or higher	12.85 or higher	12.80 or higher
75%	12.40	12.65	12.60
50%	12.20	12.35	12.30
25%	12.00	12.00	12.00
0%	11.80	11.80	11.80

NOTE: Divide values in half for 6-volt batteries.

**The "true" O.C.V. of a battery can only be determined after the battery has been removed from the load (charge or discharge) for 24 hours.*